

VAN GOGH

TECHNICAL DATA



	Standard	Result
Thickness	3mm	
Wear layer	0.5mm	
Guarantee	Commercial Heavy Duty 10 Years* Domestic Heavy Duty 15 Years*	
Bevelled edge	No	
Standards	EN 649 ASTM F-1700	
Classification	Commercial Heavy Duty use Domestic Extra Heavy Duty use	
Reaction to fire	AS 9239.1: 2003	CRF: 9.4 kW/m ² Smoke value: 84% min.
Slip resistance	AS/NZS 4586: 2004	
Staining resistance	EN 423 ASTM F-925	Class 0 Pass
Light fastness	ISO 105-B02 ASTM F-1515	≤ 7 < 8
Abrasion resistance	EN 660-2 ASTM 3884	Group T Pass
Dimensional stability	EN 434 ASTM F-2199	≤ 0.25% Pass
Acoustic impact noise reduction	EN ISO 140-8 EN ISO 717-2	$\Delta L_m = 2dB^1$
Electrical behaviour body voltage	EN 1815	Pass
Indentation – residual	EN 433 ASTM F-1914	≤ 0.1mm < 8%
Castor chair continuous use	EN 425	Pass
Thermal conductivity Suitable for underfloor heating	ISO 8302	0.0147kW/m ²
Adhesive	General use: Karndean Mega-Bond High temperature: Karndean 8000 2-part Polyurethane	
Recycling		Suitable

Product Code	Size (mm)	Slip Resistance	
		Oil-Wet Ramp	Wet Pendulum
VGW39T, VGW41T, VGW42T, VGW44T, VGW48T, VGW49T, VGW50T, VGW51T, VGW52T, VGW53T, VGW54T, VGW70T, VGW71T, VGW72T, VGW74T, VGW75T, VGW76T	1219 x 178	R11	W
VG1-7, VG5-7, VGW33T, VGW38T, VGW40T, VGW80T, VGW84T, VGW86T, VGW87T		R10	Y

For full test results please contact Karndean International.

* Subject to terms

¹ Result is $L_{n,w} + C^1 = 57dB$ when installed on Regupol 4515 acoustic underlay

FOR MORE INFORMATION :

Australia

Freecall: 1800 33 11 70

Email: enquiries@karndean.com.au

Website: www.karndean.com.au

New Zealand

Freecall: 0800 44 21 01

Email: info@karndean.co.nz

Visit: www.karndean.co.nz



Manufactured to:

